

Number	Trademark	Chemical Composition(Wt%)										
		C	Mn	Si	P	S	Ni	Cr	Mo	Cu	N	Other
1	022Cr22Ni5Mo3N S31803/F51	≤ 0.03	≤ 2.00	≤ 0.75	≤ 0.030	≤ 0.008	4.50~6.50	21.00~23.00	2.50~3.50		0.08~0.20	PREN≥34
2	022Cr23Ni5Mo3N 2205/F60	≤ 0.03	≤ 2.00	≤ 0.75	≤ 0.030	≤ 0.008	4.50~6.50	22.00~23.00	3.00~3.50	—	0.14~0.20	PREN≥35
3	022Cr25Ni6Mo2N S22553/F50	≤ 0.03	≤ 2.00	≤ 0.75	≤ 0.045	≤ 0.008	5.50~6.50	24.00~26.00	1.20~2.00		0.14~0.20	
4	03Cr25Ni6Mo3Cu2N S32554/F61	≤ 0.04	≤ 1.50	≤ 0.75	≤ 0.040	≤ 0.008	4.50~6.50	24.00~27.00	2.90~3.90	1.50~2.50	0.10~0.25	
5	022Cr25Ni7Mo4N S32750/F53	≤ 0.03	≤ 1.20	≤ 0.70	≤ 0.035	≤ 0.08	6.00~8.00	24.00~26.00	3.00~5.00	≤0.50	0.24~0.32	PREN≥41
6	022Cr25Ni7Mo4WcuN S32760/F55	≤ 0.03	≤ 1.00	≤ 0.75	≤ 0.030	≤ 0.008	6.00~8.00	24.00~26.00	3.00~4.00	0.5~1.0	0.20~0.30	W:0.50~1.00 PREN≥40